

## **TECHNICAL INFORMATION**

## BIG HORN<sup>®</sup> 200

**Description:** BIG HORN® 200 is a specially sized pure sodium bentonite for use in binding, sealing, absorbing

and general applications.

**Typical Characteristics:** Bulk Density (lbs/ft<sup>3</sup>):  $52 \pm 3$ 

**Cation Exchange Capacity** 70 – 90

(CEC meq(100gm):

Color: Light Grey to Tan

Free Swell (cc/2gm):  $20 \pm 4$  Moisture Content (%): 6 - 10 pH:  $9.1 \pm 0.4$ 

Sieve Analysis >73

(% Passing #200 Sieve):

**Specific Gravity:**  $2.55 \pm 0.1$ 

Surface Area (m<sup>2</sup>/gm): External Surface – 82

All Surfaces - 800

**Thermal Conductivity** Dry - 0.20

(Btu/hr-ft- $^{0}$ F): Saturated – 0.50

**Wet Screen Analysis**  $3.0 \pm 0.5$ 

(% Residue on #200 Sieve):

Typical Chemical Analysis:	%	
SiO <sub>2</sub>	60.34	
Al <sub>2</sub> O <sub>3</sub>	19.28	
Fe <sub>2</sub> O <sub>3</sub>	3.48	
Na₂O	2.34	
TiO <sub>2</sub>	.22	
CaO	.38	
MgO	1.67	
K <sub>2</sub> O	.10	
H <sub>2</sub> O	7.75	
Other	.07	
L.O.I.	4.37	

E.P.A Toxicity Analysis:	E.P.A Standard (ppm)	Typical Analysis (ppm)
Arsenic	5.0	<0.1
Barium	100.0	0.5
Cadmium	1.0	<0.05
Chromium	5.0	<0.1
Lead	5.0	<0.1
Mercury	0.2	<0.02
Selenium	1.0	<0.05
Silver	5.0	<0.1

Rev 3/17

WYO-BEN, INC., Billings, Montana 800.548.7055 406.652.6351 www.wyoben.com