



TECHNICAL INFORMATION



ENVIROPLUG® 16

Description: ENVIROPLUG® 16 is a specially sized, high swelling, sodium bentonite for use well sealing and can be used dry or in a pumpable slurry.

Typical Characteristics:	Bulk Density (lbs./ft³):	63 ± 3
	Cation Exchange Capacity (CEC meq(100gm):	70 – 90
	Colloid Content (%):	>85
	Color:	Light Grey to Tan
	Free Swell (cc/2gm):	>16
	Moisture Content (%):	6 - 10
	pH:	9.1 ± 0.4
	Resistivity:	2.40 ohm-meters
	Specific Gravity:	2.55 ± 0.1
	Thermal Conductivity: (Btu/hr-ft-°F):	Dry – 0.20 Saturated – 0.50

Typical Sieve Analysis:	Sieve Size	% Retained
	#8	0.92
	#20	75.67
	#30	17.35
	#100	5.29
	Pan	0.67

Typical Chemical Analysis:	%
SiO ₂	60.34
Al ₂ O ₃	19.28
Fe ₂ O ₃	3.48
Na ₂ O	2.34
TiO ₂	.22
CaO	.38
MgO	1.67
K ₂ O	.10
H ₂ O	7.75
Other	.07
L.O.I.	4.37

E.P.A Toxicity Analysis:	E.P.A Standard (ppm)	Typical Analysis (ppm)
Arsenic	5.0	<0.1
Barium	100.0	0.5
Cadmium	1.0	<0.05
Chromium	5.0	<0.1
Lead	5.0	<0.1
Mercury	0.2	<0.02
Selenium	1.0	<0.05
Silver	5.0	<0.1

Rev 3/17