

## **TECHNICAL INFORMATION**



## ENVIROPLUG GROUT<sup>®</sup>

**Description:** ENVIROPLUG GROUT® is a specially formulated 30% solids bentonite product for use in sealing

and abandonment of water wells, monitor wells and other geotechnical applications

**Typical Characteristics:** Bulk Density (lbs./ft<sup>3</sup>):  $58 \pm 4$ 

Color:

Cation Exchange Capacity

(CEC meq(100gm):

Light Grey to Tan

70 - 90

>79

Moisture Content (%): 5-12Permeability (cm/sec):  $1 \times 10^{-8}$ pH:  $8.9 \pm 0.9$ 

Sieve Analysis

(% Passing #200 Sieve):

**Specific Gravity:**  $2.55 \pm 0.1$ 

Surface Area External Surface – 82 (m²/gm): All Surfaces - 800

Thermal Conductivity 0.43

(Btu/hr-ft-<sup>0</sup>F):

**Wet Screen Analysis**  $3.0 \pm 0.5$ 

(Residue on #200 Sieve):

Typical Chemical Analysis:	%
SiO <sub>2</sub>	60.34
Al <sub>2</sub> O <sub>3</sub>	19.28
Fe <sub>2</sub> O <sub>3</sub>	3.48
Na₂O	2.34
TiO <sub>2</sub>	.22
CaO	.38
MgO	1.67
K <sub>2</sub> O	.10
H₂O	7.75
Other	.07
L.O.I.	4.37

E.P.A Toxicity Analysis:	E.P.A Standard (ppm)	Typical Analysis (ppm)
Arsenic	5.0	<0.1
Barium	100.0	0.5
Cadmium	1.0	<0.05
Chromium	5.0	<0.1
Lead	5.0	<0.1
Mercury	0.2	<0.02
Selenium	1.0	<0.05
Silver	5.0	<0.1

Rev 3/17

WYO-BEN, INC., Billings, Montana

800.548.7055

406.652.6351

www.wyoben.com