

THERM-EX GROUT™ & PowerTEC



Product Information

Description

THERM-EX GROUT™ & PowerTEC is an engineered system for use as backfill material in earth-coupled heat pump systems. Its elevated thermal conductivity and low permeability allow for excellent heat exchange while protecting groundwater supplies. THERM-EX GROUT™& PowerTEC should be pumped using a positive displacement pump capable of generating pressures in excess of 300 psi. Developed using high swelling Wyoming Bentonite, this new generation of grouting material offers efficient installation of closed-loop geothermal heat pump systems.

Material Specifications

Thermal Conductivity	.88 Btu/hr-ft-°F	1.00 Btu/hr-ft-°F	1.2 Btu/hr-ft-°F	1.4 Btu/hr-ft-°F	1.6 Btu/hr-ft-°F
Permeability	<1 X 10 ⁻⁷ cm/s				
Solid Content	32.66%	32.41%	34.54%	34.13%	36.30%
Slurry Weight	10.4 lbs/gal	10.4 lbs/gal	10.5 lbs/gal	10.5 lbs/gal	10.6 lbs/gal
Slurry Volume/Batch	53.4 gallons	39.2 gallons	36.4 gallons	59.7 gallons	55.5 gallons

Application

Thermal Conductivity	.88 Btu/hr-ft-°F	1.00 Btu/hr-ft-°F	1.2 Btu/hr-ft-°F	1.4 Btu/hr-ft-°F	1.6 Btu/hr-ft-°F
Water	45 gallons	33 gallons	30 gallons	49.5 gallons	45 gallons
PowerTEC	32 lbs	32 lbs	32 lbs	64 lbs	64 lbs
THERM-EX GROUT™	3– 50 lb bag	2 – 50 lb bag	2 – 50 lb bag	3– 50 lb bag	3 – 50 lb bag

Add the **PowerTEC** to the water while agitating and then add the **THERM-EX GROUT™**. Agitate the mixture until uniformly dispersed (2 − 3 minutes) and pump into place using a tremie line. For best results, place the tremie line near the bottom of the loop and pump into place. Providing local regulations allow, slowly extracting the tremie line as you come up the hole reduces pump pressure, aids the grout in setting quicker, and reduces the opportunity for formation damage.

Note: As correct water addition rate is critical to resulting thermal conductivity we highly recommend the use of a water meter.

Packaging THERM-EX GROUT™ is packaged in 50 pound bags.

PowerTEC is packaged in 32 pound bags.

WYO-BEN, INC., Billings, Montana

800.548.7055

406.652.6351

www.wyoben.com

The information and data made herein are believed to be accurate. As Wyo-Ben, Inc. has no control over use or application of this product, it is sold without warranty or guarantee of results.